CONCRETE INSPECTION



A complete kit for the instant and precise measurement of moisture content in concrete slabs and giving comparative readings in other cementitious floor screeds. Allowing for testing per international standards BS 8201, 8203, 5325 and ASTM F2659 & F2170, the Concrete Inspection Kit comes in a protective heavy-duty carrying case with die-cut foam lining.



KIT CONTENTS

- 1. CMEX II concrete meter.
- 2. 4 x Hygro-i2 * Relative Humidity probe.
- 3. 12 x Hole liners.
- 4. 1 x SAL75 (Calibration Check Salts)
- Infrared thermometer

Product Code: CIK5.2

FEATURES OF CMEX II

- Measures up to 6.9% Moisture Content in concrete.
- CM Carbide Method moisture content equivalent readings.
- Large clear backlit digital display.
- Hold function "freezes" meter reading when inspecting areas where the meter face is not visible.
- Attaches to a relative humidity Hygro-i2° probe for in situ testing of concrete and ambient conditions.
- 7% to 24.9% Moisture Content measurement in Wood, 7 100 WME using Pin-type probe attachment. (optional)

MEASURING RANGE SPECIFICATIONS OF KIT Depth of penetration in concrete: (NDT*) approx. 20 mm (3/4") Size: 430mm x 345mm x 130mm (16.9" x 13.6" x 5.1") Moisture content for concrete: (NDT*) 0 to 6.9% Weight: 3.65kg (8.1lbs) 0 to 4.3 Carbide Method Equivalent for concrete: Power: 2 x 9 volt PP3 Batteries (included) Carbide Method Equivalent for Anhydrite screeds (NDT*) 0 to 2.7 0 to 100 Reference scale: (NDT*) Relative Humidity with Hygro-i2 * probe: 0 to 99% 0% to 99%RH +/- 2% @ 25°C / 77°F Humidity accuracy:

*NDT - Non-destructive Test



CIK5.2-UK 08/18 REV.1.1

ASTM F2659

ASTM F2170 & BS 8201

TRAMEX Ltd.

Unit F, Glencormack Business Park, Kilmacanogue, Co.Wicklow, Ireland. Tel: +353 1 681 4450 | Fax: +353 1 282 7880 | Email: sales@tramexmeters.com

www.tramexmeters.com