

MOISTURE METER FOR CONCRETE



Instant and non-destructive tests per ASTM F2659 with the Tramex CME4, a non-invasive handheld electronic instrument used for testing moisture conditions in concrete slabs and giving comparative readings in other cementitious floor screeds. Precise and easy to use, the CME4 allows the user to make multiple tests over a large area in the shortest possible time.



Don't take risks with excess moisture!

Moisture test before you install a floor covering.



CME4 Calibration check plate CALCRH

CME4-US 09/18 REV.1.1





ASTM F2659



- Clear easy-to-read analog dial.
- No need to probe, drill or mechanically damage the surface.
- Instant and precise readings to a depth of approx. ³/₄" into the slab.
- Non-destructive in operation.
- Hold function "freezes" meter reading when inspecting areas where the meter face is not visible, and for easy recording of data.
- Reproducible results.
- Spring-loaded contact pins compensate for uneven concrete and boost signal penetration.



www.tramexmeters.com

PRODUCT DESIGN

The CME4 Concrete Encounter detects and evaluates the moisture conditions within the slab or screed by non-destructively measuring the electrical impedance. A low frequency electronic signal is transmitted into the material under test via the electrodes in the base of the instrument. The strength of this signal varies in proportion to the amount of moisture present in the material. The CME4 determines the strength of the current and converts this to a moisture content value for concrete slabs and a comparative value for other cementitious floor screeds, displayed on a large clear analog dial.

OPERATING PROCEDURE

To carry out tests simply brush any dust from a smooth area of concrete and also from the electrodes, switch on the Concrete Encounter CME4 and place it firmly onto the surface, fully compressing the spring-loaded, signal-enhancing contacts on the base. Read the moisture content from the clear analog dial.

The CME4 is calibrated to give percentage moisture content readings on clean, bare dust free concrete floor slabs, with a depth of penetration of approx. ³/₄". Readings taken on concrete slabs through paint, coatings, adhesives or other materials on the surface should be regarded as qualitative or comparative and not quantitative.

SPECIFICATIONS

Size:	6" x
Weight:	
Construction:	
Power:	
Display:	
Depth of penetration:	

3.5" x 1.5" (150mm x 85mm x 38mm) 9.84oz (279g) ABS Body 9 volt PP3 Batter y (included) Analog approx. ³⁄4" (20 mm)

MEASURING RANGE

Moisture Content for Concrete Comparative for Gypsum floor screed Reference scale 0 to 6%

0 to 10

0 to 100

HOW IT WORKS



